



Cristex Composite Materials

Product: **E 193 T**

Technical Data:

Composition ISO 7211-2			
Yarn	Warp Weft	EC9 - 68 EC9 - 68	ISO 7211-2
Thread Count	Warp Weft	14.0 ± 0.3 14.0 ± 0.3	ISO 7211-2
Tensile Strength (TYPICAL)	Warp Weft	29 kg/cm 27 kg/cm	ISO 4606
Weight		196 g/m ² ± 10	ISO 3374
Weave		Plain	
Loss on Ignition %		0.10 ± 0.04	ISO 1887

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user