

EN

Product Information

Elan-tech®

EC 180/W 340 100:36

2-component high thermal resistance epoxy system

ELANTAS Italia S.r.l.

Strada Antolini n°1 loc. Lemignano
43044 Collecchio (PR)

Italy

Tel +39 0521 304777

Fax +39 0521 804410

EEMEurope.ELANTAS@altana.com

info.elantas.italia@altana.com

www.elantas.com

Resin
EC 180

Hardener
W 340

Mixing ratio by weight
100:36

Application: Moulds for pre-pregs tools, Medium and large size heat resistant moulds up to 180°C. Composite parts thermal resistant

Processing: Impregnation manual by roll, hand-lay up applications with vacuum bag for glass, carbon or kevlar fibers. The post-curing in temperature is necessary to obtain the thermal resistance indicated. The system cured at RT remain brittle and is necessary the first curing of 16 hrs at 40°C before demoulding the model.

Description: Un-filled epoxy system. High thermal resistance.

TYPICAL SYSTEM CHARACTERISTICS

Resin

Resin Colour			Amber	
Viscosity 25°C	IO-10-50 (ISO3219)	mPas	3500	5000
Density 25°C	IO-10-51 (ASTM D 1475)	g/ml	1,17	1,21

Hardener

Hardener Colour			Pale/yellow	
Viscosity at: 25°C	IO-10-50 (ISO3219)	mPas	45	55
Density 25°C	IO-10-51 (ASTM D 1475)	g/ml	0,92	0,94

Processing Data

Mixing ratio by weight	for 100 g resin	g	100:36	
Mixing ratio by volume	for 100 ml resin	ml	100:46	
Pot life	25°C (40mm;100ml)	IO-10-53 (*)	min	220 260
Exothermic peak	25°C (40mm;100ml)	IO-10-53 (*)	°C	130 140
Initial mixture viscosity at:	25°C	IO-10-50 (ISO3219)	mPas	800 1.100
	40°C		mPas	200 300
Gelation time	25°C (1mm)	IO-10-73 (*)	h	7 9
	40°C (1mm)		h	4 6
Demoulding time	40°C (1mm)	(*)	h	14 18
Suggested curing cycles		(**)	16 h at 40°C + 10°C/h ramp + 2 h at 160°C	

EC 180/W 340

TYPICAL CURED SYSTEM PROPERTIES

Properties determined on specimens cured: 16 h at 40°C + 10°C/h ramp + 2 h at 160°C

Density 25°C		IO-10-54 (ASTM D 792)	g/ml	1,14	1,18
Hardness 25°C		IO-10-58 (ASTM D 2240)	Shore D/15	91	95
Glass transition (Tg)	16 hrs at 40°C	IO-10-69 (ASTM D 3418)	°C	72	78
	16 hrs at 60°C			90	96
	16 hrs at 40°C + 3hrs at 160°C			182	188
Maximum Tg		IO-10-69 (ASTM D 3418)	°C	--	188
Linear thermal expansion (Tg -10°C)		IO-10-71 (ASTM E 831)	10 ⁻⁶ /°C	50	58
Linear thermal expansion (Tg +10°C)		IO-10-71 (ASTM E 831)	10 ⁻⁶ /°C	130	150
Flexural strength			MN/m ²	106	120
Strain at break			%	3,0	5,0
Flexural elastic modulus			MN/m ²	3.200	3.500
Tensile strength			MN/m ²	54	60
Elongation at break			%	2,5	4,0

IO-00-00 = Elantas Italia's test method. The correspondent international method is indicated whenever possible.

nd = not determined na = not applicable RT = TA = laboratory room temperature (23±2°C)

Conversion units: 1 mPas = 1 cPs 1MN/m² = 10 kg/cm² = 1 MPa

(*) for larger quantities pot life is shorter and exothermic peak increases

(**) the brackets mean optionality

(***) The maximum operating temperature is given on the basis of laboratory information available being it function of the curing conditions used and of the type of coupled materials. For further possible information see post-curing paragraph.

EC 180/W 340

Instructions: Verify and when necessary, homogenize the components before use. Add the appropriate quantity of hardener to the resin, mix carefully. Avoid air trapping. Apply. For the surface preparation (mould or model) refer to the release agents data sheet.

Curing / Post-curing: Prior to demould from the model cure the material at least for 16-12 hrs at 35-40°C. Post curing is always advisable for RT curing systems in order to stabilize the component and to reach the best properties. It is necessary when the component works at a high temperature. Post cure the tool as stated in the table, increasing gradually 10°C/hour. Cool it down slowly. The rate of heating and the indicated post-curing time are referred to standard specimen size. Users should evaluate the best conditions of curing or post-curing depending on the component size and shape. For big size components decrease the thermal gradient and increase the post-curing time.

Storage: Epoxy resins and their hardeners can be stored for one years and two year respectively in the original sealed containers stored in a cool, dry place. Resin storage must be done at 10-20°C. The hardeners are moisture sensitive therefore it is good practice to close the container immediately after each use. The hardeners may crystallize at low temperatures. To restore the original conditions, heat the material at 40-50°C avoiding local overheating. Before use the product must be cooled down at room temperature.

Handling precautions: Refer to the safety data sheet and comply with regulations relating to industrial health and waste disposal.

emission date: March 2014
revision n° 00

The information given in this publication is based on the present state of our technical knowledge but buyers and users should make their own assessments of our products under their own application conditions.

EC 180/W 340

Graphic 1 – Mixed Viscosity of the System EC 180/W 340 at different temperatures

