



## TECHNICAL DATA SHEET

**SAP No.** 30002640      **Article Description** X-C-218g/m<sup>2</sup>-1400mm

**Textile Structure** 7003065

| ARTICLE CONSTRUCTION (in accordance with EN 13473-1) |              |                      |           |                            |
|------------------------------------------------------|--------------|----------------------|-----------|----------------------------|
| Layer                                                | Construction | Areal weight         | Tolerance | Material                   |
| 2                                                    | 45 °         | 107 g/m <sup>2</sup> | +/- 5 %   | TORAY T700SC 50C 12K       |
| 1                                                    | -45 °        | 107 g/m <sup>2</sup> | +/- 5 %   | TORAY T700SC 50C 12K       |
| Stitching                                            |              | 4 g/m <sup>2</sup>   | +/- 1 %   | PES (Polyester 48) dtex SC |

| FURTHER CHARACTERISTICS |         |                          |       |                           |                      |
|-------------------------|---------|--------------------------|-------|---------------------------|----------------------|
| <b>Gauge</b>            | 5,0     | <b>Stitching pattern</b> | warp  | <b>Width (nominal)</b>    | 1,400 mm             |
| <b>Stitch length</b>    | 2,60 mm | <b>Total tolerance</b>   | 5,4 % | <b>Total areal weight</b> | 218 g/m <sup>2</sup> |

- Labelling (Standard)**      Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.
- Packaging (Standard)**      Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.
- Storage**      With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.