



TECHNICAL DATA SHEET

SAP No. 30004156 **Article Description** Q-C-816g/m²-1270mm

Textile Structure 7004264

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)				
Layer	Construction	Areal weight	Tolerance	Material
4	0 °	205 g/m ²	+/- 5 %	AKSA A-42 12K
3	45 °	200 g/m ²	+/- 5 %	AKSA A-42 12K
2	90 °	205 g/m ²	+/- 5 %	AKSA A-42 12K
1	-45°	200 g/m ²	+/- 5 %	AKSA A-42 12K
Stitching		6 g/m ²	+/- 1 %	PES (Polyester) 74 dtex SC

FURTHER CHARACTERISTICS					
Gauge	5,0	Stitching pattern	Tricot	Width (nominal)	1,270 mm
Stitch length	2,60 mm	Total tolerance	5,1 %	Total areal weight	816 g/m ²

Labelling (Standard)

Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard)

Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage

With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.