



WOVEN FABRIC TECHNICAL DATA SHEET

Product Reference: GG 1200 T

Characteristics		Nominal	Tolerance	Normative
Mass per unit area	g/m ²	1184	± 5%	ISO 4605
Weave		2/2 Twill		ISO 2113
Width	mm	1000	± 2,5%	ISO 22198
Thickness	mm		± 2,5%	ISO 5084(**)
Other information		Loomstate		

Nominal Construction		Warp		Weft	
Fibre Description		HR Carbon Fibre 24K – 1600 tex		HR Carbon Fibre 24K – 1600 tex	
Fibre Producer		TORAY		TORAY	
Thread Count	ends/cm	3,7	ISO 4602	3,7	ISO 4602
Weight Distribution	g/m ²	24K	592	24K	592
	%	Carbon	50%	Carbon	50%
Selvedges		Weaving Style	LENO	Type of Fibre	HM Polyester 22 tex

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.



(**) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.



Cristex Composite Materials
COMPOSITES YOU CAN TRUST

Cristex Composite Materials

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

West House | Shadsworth Business Park | off Duttons Way | Blackburn | Lancashire | BB1 2QJ

T: 01282 770666 | E: sales@crístex.co.uk | W: www.cristex.co.uk

 cristexltd  Crístex Composites  Crístex Composite Materials