

## WOVEN TAPE TECHNICAL DATA SHEET

**Product Reference:** TVU 400

Characteristics		Nominal	Tolerance	Normative
<b>Mass per unit area</b>	g/m <sup>2</sup>	400	± 5%	ISO 4605
<b>Weave</b>		Plain		ISO 2113
<b>Standard Width</b>	mm	From 10 mm to 200 mm	± 2,5%	
<b>Laminate Thickness</b>	mm	0,40	± 2,5%	ISO 5084(**)

Nominal Construction		Warp		Weft	
<b>Fibre Description</b>		Glass Roving 300 tex		Glass Fibre EC 9 68 tex	
<b>Thread Count</b>	ends/cm	12,0	ISO 4602	3,0 x 2	ISO 4602
<b>Weight Distribution</b>	g/m <sup>2</sup>	Glass Roving	360	Glass Fibre	40
	%		90%		10%

(\*\*) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

**Note:** Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.